ABSRACT OF THE DISCLOSURE

A molding composition comprising an aggregate [Component (A)], a linear unsaturated polyester [Component (B)] and/or linear unsaturated polyester polyamide [Component (C)], and a radical generator [Component [D]), characterized in that each of Component (B) and Component (C) comprises a specific alkylene oxide adduct of bisphenol A in an amount of from 3 to 50 mol% based on the total amount of constituent monomers of each of Component (B) and Component (C), and a molded article obtained by molding the composition.